

Cr and Mo-alloyed electrode for heat resistant steels.

STARBLAZE PRIME 9015-B9

Classification

AWS A 5.5: E9015-B91

EN ISO 3580-A: E CrMo91 B 4 2 H5

Description and applications

Basic coated extra low hydrogen electrode for welding high temperature creep resistant steels type 9 Cr-1Mo-V-Nb-N with operating temperatures up to +620°C. Best suitable for welding of P91, T91 and F91 type of steels. Excellent weldability, self-peeling slag, finely rippled weld bead. Welds are of radiographic quality. Used for turbine rotors, petrochemicals plants, thermoelectric power plants.....etc.

Base materials

T91(ASTM A213), F91(ASTM A182), P91(ASTM A335), grade 91 (ASTM A 387), X10CrMoVNb9-1

Typical weld metal Chemical Composition (%)

C	Si	Mn	Cr	Mo	Ni	S	P	V	Nb	N
0.10	0.20	0.60	9.00	1.00	0.60	≤0.010	≤0.010	0.20	0.050	0.04

Diffusible hydrogen (Per 100gm weld metal):	< 4 ml.
---	---------

All weld metal mechanical properties (typical)

Heat Treatment	Yield strength R _p (N/mm ²)	Tensile strength R _m (N/mm ²)	Elongation A5 (%)	Impact Energy ISO-V(J)+20°C
PWHT 760°C X 2h	≥ 550	≥ 650	≥18	≥47


Amperes (A)

2.50mm	3.15mm	4.0mm	5.0mm
60- 90	90- 120	140- 180	180- 220

Welding instruction

Storage and re-drying: Keep dry and avoid condensation. Redry electrodes at 300 – 350°C for 1 hour.

Welding positions



Stellaris Specialities India Ltd.

(Division: StarBlaze India)

GST No.: 06AAICS2482B1ZK / Legal Metrology No.: GOI/DL/2022/4850

Plant 1: A-125, Okhla Industrial Area, Phase 2, New Delhi - 110020

Corporate Office & Plant 2: 552, Pace City II, Sector 37, Gurugram, Haryana - 122001

Plant 3: B-100, Mayapuri Industrial Area, Phase-1, Near Police Station, New Delhi-110064

Plant 4: A-334, RIICO Industrial Area, Karoli, Bhiwadi, Rajasthan - 301707

Tel: +91 124 4499523 | Email: sales@starblazeindia.com | Website: www.starblazeindia.com